

# Technical Data Sheet

## PGR 3200

### Product Description

PGR 3200 is produced of rubber granules. The product is obtained by adding a PUR binder to the rubber granules and compressing them in a mould to the target density.

### Technical specifications

Properties	Specifications	Unit	Method
Density	700 - 800	kg/m <sup>3</sup>	ISO 845
Tensile Strength	> 500	kPa	ISO 1798
Elongation	> 40	%	ISO 1798
Median Heat Transfer Resistance	0,0480	m <sup>2</sup> K/W	ISO 8302
Median Theoretical Heat Transfer Coefficient	0,1046	W/mK	ISO 8302
Fire classification	E		ISO 11 925-2
Impact Sound Improvement Level $\Delta L_w$	approx. 21	dB	ISO 140-8



**RECTICEL International**

Damstraat 2  
B-9230 Wetteren  
T. +32 9 368 92 11  
Belgium

published on: 10/2011

All data are typical values provided by our internal control system